

Material Natural rubber latex, in compliance with ASTM D1076

Dimensional Specifications

SIZE	Minimum Length mm (inches)	Average Palm Width mm (inches)
Small	240 (9.4)	85 (3.3)
Medium	240 (9.4)	95 (3.7)
Large	240 (9.4)	106 (4.2)

Thickness (single)

Data from Sampling	Average Thickness
Fingertip, mm (mils)	0.14 (5.5)
Palm, mm (mils)	0.12 (4.7)
Cuff, mm (mils)	0.10 (3.9)

Physical Properties (ASTM Requirements)

	Before Aging	After Aging
Freedom from Holes (inspection level 1)	2.5 AQL*	N/A
Tensile, MPa (p.s.i.) minimum	18.0 (2,611)	14.0 (2,031)
Elongation (%) minimum	650	500

Ansell manufacturing specifications meet or exceed ASTM specifications.

Color	Cream
Accelerators	Zinc dibutyldithiocarbamate (ZDBC) Zinc diethyldithiocarbamate (ZDEC)
Certification	Manufacturing facility registered to ISO 9001 and ISO 13485
Donning Agent	Polymer coating (powder-free)
Residual Powder Content	<2.0 mg/glove
Quality Control	In compliance with ASTM D3578 examination glove standards
References	ANSI/ASQ Z1.4 Sampling Procedures and Tables for Inspection by Attributes
Country of Origin	Malaysia
Storage	Cool environment, shielded from ozone and UV light

*Acceptable quality level – maximum % of gloves with defects

For additional information and samples, call Ansell at 800-952-9916 or visit us at www.ansellhealthcare.com

Ansell Healthcare Products LLC | ansellhealthcare.com
200 Schulz Drive | Red Bank, NJ 07701 U.S.A. | Phone: (800) 952-9916 (U.S.A. only)
Ansell and Micro-Touch are registered trademarks owned by Ansell Limited or one of its affiliates. ©2011 Ansell Healthcare Products LLC. All Rights Reserved.

SS540 04/2011